Reactive Red FBN C.I. Reactive Red 180A

Light : 5 : 4 - Effect Washing < Stain : 4-5 Perspiration Acidic : 4-5 Bleaching Hypochlorite : 2-3 Chlorinated Water : 3-4 Dischargeability : Poor Solubility at 60°C : 100 g/l 1% Cotton Dyeing
4% Cotton Printing
2% Discharge Printing

Reactive Red BB C.I. Reactive Red 121

: 5 Light Effect : 4-5 Washing — Stain 4-5 : 4-5 Perspiration Acidic Bleaching Hypochlorite : 1 : 2 Chlorinated Water : Good Dischargeability Solubility at 60°C : 100 g/l



1% Cotton Dyeing