

Reactive Yellow ME4GL
C.I. Reactive Yellow 186

Light	:	5-6
Washing	Effect	: 4
	Stain	: 4-5
Bleaching	Hypochlorite	: 1
	Peroxide	: 3-4
Perspiration (Acidic)	Effect	: 4-5
	Stain	: 4-5
Dischargeability	:	Good
Solubility at 60°C	:	100 g/l

Not suitable for silicate Pad-batch method.

1% Cotton Dyeing
4% Cotton Dyeing
1% Hosiery Dyeing
4% Hosiery Dyeing



Reactive Yellow 3RX 150%
C.I. Reactive Yellow 145 A

Light	:	6-7
Washing	Effect	: 4
	Stain	: 4-5
Bleaching	Hypochlorite	: 1
	Peroxide	: 4
Perspiration (Acidic)	Effect	: 4
	Stain	: 4-5
Dischargeability	:	Good
Solubility at 60°C	:	100 g/l

1% Cotton Dyeing
4% Cotton Dyeing
1% Hosiery Dyeing
4% Hosiery Dyeing

